



# AMP-UP™ RB

AMP-UP™ RB is a single component, environmentally friendly, self-healing, water-based rebar protection solution. AMP-UP™ RB is designed for protecting reinforcing or structural steel before, during, and after application of concrete. AMP-UP™ RB utilizes patented self-healing technology that helps maintain adhesion and corrosion resistance on rebar subject to damage.

## Features

- ✓ One-component system
- ✓ Long Lasting Corrosion Protection
- ✓ Low VOC (< 50 g/L)
- ✓ Long Recoat Window
- ✓ Patented self-healing technology

## Surface Preparation

**All Surfaces:** Remove dirt, dust, oil, salt, and any other chemical contaminants by washing the surface with a cleaner/degreaser and water. Mold and mildew areas must be cleaned with a chlorinated cleaner or bleach solution. Rinse thoroughly with fresh water and allow to fully dry. All surfaces must be dry at time of application.

**Reinforcing or Structural Steel:** Remove loose rust, mill scale and coatings in accordance with hand tool (SSPC-SP-2) or power tool (SSPCSP-3) cleaning. For optimum corrosion performance, abrasive blast to SSPC-SP-6 Commercial Grade is recommended.

**Concrete and Masonry:** Remove weak or deteriorated concrete and masonry to obtain sound surface. Remove dirt, dust and other contamination from the surface by air blowing, brushing, scrubbing or other acceptable method. Avoid leaving cleaner residues on the surface of the concrete if used.

## Equipment Recommendations

**Brush:** Use a good quality synthetic bristle brush.

**Roller:** Use a good quality synthetic nap roller cover.

## Thinning

Thinning is normally not required. Thin with water as needed for desired application viscosity (up to 1 pint per gallon).

## Clean-up

Use soap and water immediately after use.

## Rebar Coverage

IMPERIAL BAR SIZE	NOMINAL DIAMETER (IN)	LINEAR COVERAGE AT 3 MILS DFT (FT)
#3	0.375	2000
#4	0.500	1500
#5	0.625	1200
#6	0.750	1000
#7	0.875	850
#8	1.000	750
#9	1.128	650
#10	1.270	600

## Performance

METRICS	METHODS	RESULTS
PENCIL HARDINESS	ASTM D3363	H (after 7 days)
FLEXIBILITY (MANDREL BEND)	ASTM D522	>40%
IMPACT RESISTANCE (DIRECT)	ASTM D2794	100 inch-lbs
TABER ABRASION	ASTM D4060 (CS10, 1000g, 1000 cycles)	57 mg loss
CROSS-HATCH	ASTM D3359	5B
CORROSION PERFORMANCE	ASTM B117 (1000h of exposure)	1.5 mm of creep from scribe
REBAR PULLOUT ADHESION	ASTM D7913 (#5 rebar, 28day concrete cure)	Bare: 21,510 lbs AMP-UP RB: 21,333 lbs (>99% of bare rebar adhesion)

## Physical Properties

APPLICATION CONDITIONS	TEMP RANGE	>40 °F (>4 °C)
	REL HUMIDITY	Less than 85%
	SURFACE TEMP	5°F (3°C) above dew point
RESIN TYPE		Water-Based Epoxy Amine Adduct
PIGMENT TYPE		Metal Oxides (Varies with color)
SOLVENTS		Water
WEIGHT	PER GALLON	10.4 - 10.5 lbs.
	PER LITER	1.2 - 1.3 kg
SOLIDS	BY WEIGHT	52%
	BY VOLUME	40%
VOLATILE ORGANIC COMPOUNDS		47 g/L
RECOMMENDED DRY FILM THICKNESS(DFT) PER COAT		2.0 - 3.0 mils (51- 76 µm)
WET FILM TO ACHIEVE DFT		5.0 - 8.0 mils (127 - 203 µm)
COVERAGE AT RECOMMENDED DFT		200 - 320 sq. ft./gal. (4.9 – 7.9 m2/L)
DRY TIMES 70-80 °F (21-27°C) and 50% Relative Humidity	TACK-FREE	0.5 - 1 hour
	HANDLE	2 - 4 hours
	RECOAT	1 - 4 hours
	CONCRETE	4 hours to 180 days
DRY HEAT RESISTANCE		200°F (93°C)
SHELF LIFE		1 year (Below 40°C)
SAFETY INFORMATION		See SDS

Seller believes all technical data and other information presented herein to be reliable but are not a warranty or representation for which we assume any liability or duty of any kind. Such data and other information are intended for use only by persons having all necessary skill and know-how, at their own discretion and risk. Users are responsible to undertake such verification and testing as they determine to confirm the accuracy of such data and other information and suitability of the subject materials for their own particular purpose. SELLER DOES NOT MAKE, AND HEREBY DISCLAIMS FOR ALL PURPOSES, ALL REPRESENTATIONS AND WARRANTIES, EXPRESS OR IMPLIED, CONCERNING SUCH DATA AND OTHER INFORMATION (INCLUDING WITHOUT LIMITATION WARRANTIES OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE). Users hereby waive any claim with respect to any damages and claims of any kind or nature based on such data and other information, except as otherwise agreed in writing by a duly authorized representative of Seller.